

# Material Datasheet

## REPROgress Advanced Regrind

RGPP-0615 - A Jazz, Medium MFI PP suitable for black and dark colour compounding applications.

REPROgress Advanced Regrinds are blended, de-dusted and quality controlled regrinds for direct use in conversion processes.



Property	Test Methods	Test Conditions	Typical Values	Unit
Melt Flow Index	ISO 1133	2.16kg / 230° C	6 - 15	g/10 min
Izod Impact Strength	ISO 180	Notched, 23° C	4 - 15	KJ/m <sup>2</sup>
Ash Content	INTERNAL	600° C / 15 mins	<10	%
PE Content	INTERNAL	DSC	<8	%
Colour	Visual Inspection		Jazz	

Additional Information	Options
Packaging Types Available	25Kg Bag
	Bulk Bag
	Bulk Tanker
	Octabins

**\*\*NB\*\*** The property details shown above are typical of the material type and are for guidance only. They do not constitute specification limits. Variances from the above information may occur and no guarantee can be provided or implied due to the factors that may or will influence the processing of the material and varied material sources to produce the material. The above information does not relieve the processor(s), user(s) and product manufacturer(s) of the requirement to carry out their own specific testing.

